

Dev Priya Papers Pvt. Ltd., Meerut

Product : GALAXY

GSM Range – 250 – 450 g/m2 GREY BACK

Parameters	GSM-250 ± 3%	GSM-285 ± 3%	GSM-300 ± 3%	GSM-320 ± 3%	GSM-350 ± 3%	GSM-400 ± 3%	GSM-450 ± 3%
Brightness % (± 1%)	73	73	73	73	73	73	73
Caliper Micron (± 5%)	300	342	360	387	423	488	553
Bulk cc/gm (± 5%)	1.20	1.20	1.20	1.21	1.21	1.22	1.23
Stiffness							
MD Taber (± 10%)	80	95	120	140	165	250	300
CD Taber (± 10%)	40	45	60	70	75	120	135
Gloss %	30-35	30-35	30-35	30-35	30-35	30-35	30-35
Cobb Top g/m2	40-50	40-50	40-50	40-50	40-50	40-50	40-50
Cobb Bottom g/m2	45-50	45-50	45-50	45-50	45-50	45-50	45-50
Moisture	6.0-7.0	6.0-7.0	6.0-7.0	6.0-7.0	6.5-8.0	6.5-8.0	7.0-8.0
Wax Pick	7A	7A	7A	7A	7A	7A	7A